Format No: CP/TF/01

TEST REPORT OF PHYSICAL PROPERTIES OF CEMENT - 53 Grade

Lab ID	:	**CP-2018-12-20-112** **Date: 20-10-18**
Customer	:	Assistant Executive Engineer, Yelahanka Sub Division, BBMP, Bangalore.
Address	:	Yelahanka Sub Division, BBMP, Bangalore.
Project Name	:	Intimation of Work Order to Start the Work of Improvements to Roads and Drains at Maheshwari Nagar Cross Roads and Surrounding areas in Ward No-01 of Yelahanka Sub Division.
Agency	:	Sri.N.Shivakumara No:96,KHB Colony, Gandhinagara,Yelahanka Bangalore-64.
Customer's Reference	:	EE(YNK.D)E-PMT-19/W.O/000061/2018-19
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	17-10-18
Sample Type	:	Birla Super 53grade
Reference to BIS codes	:	IS 12269 : 2013, 53 Grade Ordinary Portland cement Specification , IS 4031 (Part 1,2 3,4,5, 6,11):1988 IS 4031 Part 1 DETERMINATION OF FINENESS BY DRY SIEVING, Clause 4.4 IS 4031 Part 2, Determination of Fineness by Blaine Air Permeability Method, Clause 5 IS 4031 Part 3, Determination of Soundness, Clause 5,Clause 6 IS 4031 Part 4, Determination of Consistency of Standard Cement Paste, Clause 5 IS 4031 Part 5, Determination of Initial & Final Setting Time, Clause 5 IS 4031 Part 11,DETERMINATION OF DENSITY , Clause 6
Date of test	:	18-10-18
Environmental Conditions during test	:	Temperature: 26°C Humidity: 72%

Sl.No.	Physical properties	Results	Requirement as per IS 12269: 2013
1	Fineness by dry sieving (%)	1.52	–
2	Finess by Air permeablity method (m^2/kg,Min)	298.3	225m^2/kg, Min
3	Density (gm/cc)	3.13	–
4	Standard Consistency (%)	29.5%	Not specified
5	Initial Setting time	165 minutes	Not less than 30 minutes
6	Final Setting time	250 minutes	Not more than 600 minutes
7	Soundness (Le Chatelier's Method)	1.5mm	Not more than 10 mm

AE-1 A.E.E

Note:

The results pertain to the samples received and tested.

All information furnished by Customer/Representative

Any correction in the report will make this report invalid

This report without prior written approval should not be reproduced or published in full or part.

Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

CIVIL Pro Sig..... Date..... BANGALORE

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Scanned by CamScanner

Format No: CP/TF/01

TEST REPORT ON COARSE AGGREGATES

Lab ID	:	**CP-2018-12-20-112** **Date: 20-10-18**
Customer	:	Assistant Executive Engineer, Yelahanka Sub Division, BBMP, Bangalore.
Address	:	Yelahanka Sub Division, BBMP, Bangalore.
Project Name	:	Intimation of Work Order to Start the Work of Improvements to Roads and Drains at Maheshwari Nagar Cross Roads and
Agency	:	Sri.N.Shivakumara No:96,KHB Colony, Gandhinagara,Yelahanka Bangalore-64.
Customer's Reference	:	EE(YNK.D)E-PMT-19/W.O/000061/2018-19
Source of Sample	:	Sample supplied by Agency
Sample condition	:	Satisfactory
Date of Receipt	:	17-10-18
Sample Type	:	40mm down size coarse aggregate
Reference to BIS codes	:	IS: 383:2016 (Specification for Coarse and fine Aggregates)
		IS: 2386 :1963(Part - 1,3,4) RA2011
		IS 2386 Part 1: Particle Size and Shape
		IS 2386 Part 3: Specific gravity, Density, Voids,Water Absorption
		IS 2386 Part 4: Mechanical Properties
Date of test	:	17-10-18

AE-I
A.E.E
AE

SIEVE ANALYSIS (PARTICLE SIZE DISTRIBUTION) OF 40MM DOWN COARSE AGGREGATE:

Total weight taken : 15000 grams

Sample No.	Sieve No.	Weight Retained in gms	Cumulative Weight Retained in gms	% Cumulative Weight Retained	% Passing	Required as per IS 383:2016
1	80 mm	0	0	0.0	100	100
2	40 mm	235	235	1.6	98.4	90-100
3	20 mm	7511	7746	51.6	48.4	30-70
4	10 mm	4102	11848	79.0	21.0	10-35
5	4.75 mm	2899	14747	98.3	1.7	0-5
6	Pan	253	15000	100.0	0	---

CIVIL Pro Sig..... Date..... BANGALORE

Scanned by CamScanner

Format No: CP/TF/01

TEST REPORT OF FINE AGGREGATE

Date: 20-10-18

Lab ID	:	**CP-2018-12-20-112**
Customer	:	Assistant Executive Engineer, Yelahanka Sub Division, BBMP, Bangalore.
Address	:	Yelahanka Sub Division, BBMP, Bangalore.
Project Name	:	Intimation of Work Order to Start the Work of Improvements to Roads and Drains at Maheshwari Nagar Cross Roads and Surrounding areas in Ward No-01 of Yelahanka Sub Division.
Agency	:	Sri.N.Shivakumara No:96,KHB Colony, Gandhinagara,Yelahanka Bangalore-64.
Customer's Reference	:	EE(YNK.D)E-PMT-19/W.O/000061/2018-19
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	17-10-18
Sample Type	:	Fine Aggregate
Reference to BIS codes	:	IS 383 : 2016 (Specification for Coarse and fine Aggregates) IS: 2386 :1963(Part - 1, 3) RA2012 IS 2386 Part 1: Particle Size and Shape IS 2386 Part 3: Specific gravity, Density, Voids,Water Absorption
Date of test	:	17-10-18
Total weight taken	:	1000 grams

Sl.no	Sieve Size	Weight Retained (gms)	Cumulative Weight Retained (gms)	% Cumulative Weight Retained	% Passing	Requirement as per IS 383:2016			
						Grading Zone I	Grading Zone II	Grading Zone III	Grading Zone IV
1	10 mm	0	0	0.0	100.0	100	100	100	100
2	4.75 mm	52	52	5.2	94.8	90-100	90-100	90-100	95-100
3	2.36 mm	144	196	19.6	80.4	60-95	75-100	85-100	95-100
4	1.18 mm	198	394	39.4	60.6	30-70	55-90	75-100	90-100
5	600 micron	201	595	59.5	40.5	15-34	35-59	60-79	80-100
6	300 micron	182	777	77.7	22.3	5-20	8-30	12-40	15-50
7	150 micron	158	935	93.5	6.5	0-10	0-10	0-10	0-15
8	Pan	65	1000	100.0	0.0	---	---	---	---

Result :The tested Sample Conforms to Grading Zone II

A.E.E

AE

CIVIL PRO Sig..... Date..... BANGALORE

Scanned by CamScanner